


# WOVEN GEOTEXTILE

## SW - 200



SKAPS woven geotextile fabrics are woven polypropylene materials offering optimum performance when used in stabilization applications. Produced from first quality raw materials, they provide the perfect balance of strength and separation in styles capable of functioning exceptionally well in a wide range of performance requirements. SKAPS SW200 resists ultraviolet resistance, rotting, biological degradation and it is chemically inert to any natural bases or acids.



Unless indicated below, all listed properties are Minimum Average Roll Values

Property	Method	English (MARV <sup>2</sup> )	Metric (MARV <sup>2</sup> )
Grab Tensile	ASTM D 4632	200 lbs.	0.9 kN
Grab Elongation	ASTM D 4632	15%	15%
Trapezoid Tear	ASTM D 4533	75 lbs.	0.33 kN
CBR Puncture Resistance	ASTM D 6241	700 lbs	3.12 kN
Water Flow <sup>3</sup>	ASTM D 4491	5 gpm/sf	203 l/min/m <sup>2</sup>
Permittivity <sup>3</sup>	ASTM D 4491	0.05 sec <sup>-1</sup>	0.05 sec <sup>-1</sup>
AOS <sup>3</sup>	ASTM D 4751	40 U.S. Sieve	0.43 mm
UV Resistance	ASTM D 4355	70%/500 hrs.	70%/500 hrs.

## Packaging

Roll Dimensions (W x L)	12.5 x 432 ft. 15 x 360 ft. 17.5 x 309 ft.	3.81 m x 132 m 4.57 m x 110 m 5.33 m x 94 m
Area Per Roll	600 sq. yards	500 sq. meters

## Note

1. The property values listed above are subject to change without notice.
2. Minimum Average Roll Values (MARV) is calculated as the average minus two standard deviations. Statistically, it yields approximately 97.5% degree of confidence that any samples taken from quality assurance testing will meet or exceed the values described above.
3. At time of manufacturing. Handling may change these properties.

*This information is provided for reference purposes only and is not intended as a warranty or guarantee. SKAPS assumes no liability in connection with the use of this information.*