

Product Specification – LEgeo BX Type 1 Geogrid

DISCLAIMER: L.E. Geosolutions, LLC reserves the right to change its product specifications at any time and without notice. It is the user’s responsibility to ensure that this specification is current and that the specified product is appropriate for the application being considered.

Product Type: Integrally formed biaxial geogrid
Polymer: Polypropylene
Load Transfer Mechanism: Positive mechanical interlock
Standard Roll Size: 13 ft x 246 ft (355 SY per roll)

Product Properties

Index Properties	Test method	Units	MD value ¹	XMD value ¹
Structural integrity				
• Aperture dimensions	Direct measurement ²	mm (in)	25 (1.0) ³	36 (1.4) ³
• Minimum rib thickness	Direct measurement ²	mm (in)	1.00 (0.04)	0.76 (0.03)
• Tensile strength @ 2% strain	ASTM D6637M-15	kN/m (lb/ft)	4.1 (280)	6.6 (450)
• Tensile strength @ 5% strain	ASTM D6637M-15	kN/m (lb/ft)	8.5 (580)	13.4 (920)
• Ultimate tensile strength	ASTM D6637M-15	kN/m (lb/ft)	12.4 (850)	19.0 (1,300)
Durability				
• Junction efficiency	ASTM D7737/D6637	%	93	
• Flexural stiffness	ASTM D7748	mg-cm	250,000	
• Aperture stability	GRI-GG9 ⁴	N-m/deg	0.32	
• Resistance to installation damage (SW/SP/GP soil)	ASTM D6637-01	%	95/93/90	
• Resistance to long-term degradation	ASTM D6637-01	%	100	
• Resistance to UV degradation	EPA9090A	%	100	

Notes:

1. Unless indicated otherwise, values shown are Minimum Average Roll Values (MARV) in accordance with ASTM D4759-02.
2. Direct Caliper Measurement.
3. Nominal values.
4. Resistance to in-plane rotational movement measured by applying a 20 kg-cm moment.
5. All LEgeo BX Type 1 geogrids are proudly manufactured in the United States of America.